

Dawnprene TPV 11-50DV

TPV

TPV

Features:

A hard,black thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material combines good physical properties,chemical resisitance and elasticity, designed for injection applications.This grade of TPV can be processed on conventional thermoplastics equipment for extrusion ,injection or blow molding .It is polyolefin based and completely recyclable.

RoHS		RoHS	
		2019-5-16	
(Shore D,5 sec,2	48.6	D	DIN 53505
100% - 2	11.6	Mpa	DIN 53504
- 2	21.4	Mpa	DIN 53504
- 2	800	%	DIN 53504
- 2	89	KN/m	DIN ISO 34-1
(150	-22.3	%	
(150	-16.4	%	DIN 53505
(150	-3	D	DIN 53504
0.01%			
Drying Instructions: Need drying the granules before make molding,excessive moisture will lead materials bad extrusion surface,mechanical performance reduction and bad surface appearance. Moisture content request below 0.01%,suggesting drying as follow process:			
Drying conditions	Dring temperature/		Dring time/h
first choice	80 90		2 3
other choice	100		1



R							
4	16 170	180-185	190-210	190-215	180-205	170-185	50-70

1. Dawnprene TPV PVC

Dawnprene TPV is incompatible with PVC materials, hence must clean the equipment before using.

2. 110 85 2 , .

Above testing data is tested by injected sample block, cutting by the sheet size is 110 85 2 .

3. 25%

Compression Set 25%

4. .

The properties is typical performance, is not regarding as technical index or agreement.

5.

Any reprocessing must follow the above instructions, and ensure no content impurity.

6.

Above instructions for reference only, different equipment might have difference parameters, please adjust accordingly with different mold and product shape.

SHANDONG DAWN POLYMER CO.,LTD

: . 265703

Address: Zhenxing Road, Longgang Economic Zone, Longkou, Shandong, China. 265703

() 0086-535-8868588; () 0086-535-8833988

Tel: (Foreign Trade) 0086-535-8868588; (Domestic Trade) 0086-535-8833988