

Dawnprene TPE 9301-PB

TPE

TPE

Features:

It is a n black colour thermoplastic elastomer (TPE) material.This material combines good physical properties,chemical resitance and elasticity, designed for injection applications.This grade of TPE can be processed on conventional thermoplastics equipment for injection molding.It is completely recyclable.

| | | | |
|---|----------------------|-------------------|------------|
| | | | |
| | | | |
| RoHS | RoHS | | |
| | | | |
| | | | |
| | 2018-03-19 | | |
| | | | |
| | 0.98 | g/cm ³ | ASTM D792 |
| MFR (190 | 34 | g/10min | ASTM D1238 |
| | | | |
| (Shore A,10 sec,2 | 94 | A | ASTM D2240 |
| | | | |
| 100% - 2 | 6.4 | Mpa | ASTM D412 |
| - 2 | 12.0 | Mpa | ASTM D412 |
| - 2 | 600 | % | ASTM D412 |
| - 2 ! ! | 75.0 | KN/m | ASTM D624 |
| <p>0.01%</p> <p>Drying Instructions: Need drying the granules before make molding,excessive moisture will lead materials bad extrusion surface,mechanical performance reduction and bad surface appearance. Moisture content request below 0.01%,suggesting drying as follow process:</p> | | | |
| Drying conditions! | Dring temperature/ ! | Dring time/h | |
| first choice! | 70 80! | 1 2 | |
| other choice! | 100! | 1 | |
| 110 | | 105 | |
| <p>If drying temperature over than 110 ,it might cause materials blocking in barrel zone;if use moisture analysis meter,the temperture setting should be on 105 .</p> | | | |

| |
|---|
| <p>1.Dawnprene TPE PVC Dawnprene TPE is incompatible with PVC mateials,hence must clean the equipment before using.</p> |
| <p>2. 110 85 2 , . Above testing data is tested by injection sample block, cutting by the sheet size is 110 85 2 .</p> |
| <p>3. 25% Compression Set 25%</p> |
| <p>4. . The properties is typical performance,is not regarding as technical index or agreement.</p> |
| <p>5. Any reprocessing must follow the above instructions,and ensure no content impurity.</p> |
| <p>6. Above instructions for reference only,different equipment might have difference parameters,please adjust accordingly with different mold and product shape.</p> |
| <p>SHANDONG DAWN POLYMER CO.,LTD : . 265703 Address:Zhenxing Road,Longgang Economic Zone,Longkou,Shandong, China. 265703 () 0086-535-8868588;()0086-535-8833988 Tel:(Foreign Trade) 0086-535-8868588;(Domestic Trade)0086-535-8833988</p> |