

# Dawnprene TPE 8001-PB

TPE

TPE

Features: It is a black colour thermoplastic elastomer (TPE) material. This material combines good physical properties, chemical resistance and elasticity, designed for injection applications. This grade of TPE can be processed on conventional thermoplastics equipment for injection. It is completely recyclable.

RoHS	RoHS		
	2019-06-10		
	0.956	g/cm <sup>3</sup>	ASTM D792
(Shore A, 10 sec, 2	81.7	A	ASTM D2240
100% 2	3.56	Mpa	ASTM D412
2	7.13	Mpa	ASTM D412
2	650	%	ASTM D412
2	51.3	KN/m	ASTM D624

0.01%

Drying Instructions: Need drying the granules before make molding, excessive moisture will lead materials bad extrusion surface, mechanical performance reduction and bad surface appearance. Moisture content request below 0.01%, suggesting drying as follow process:

Drying conditions	Dring temperature/	Dring time/h
first choice	80 90	2 3
other choice	100	1

110

105

If drying temperature over than 110 ,it might cause materials blocking in barrel zone; if use moisture analysis meter, the temperature setting should be on 105 .



R							
4	16 170	180-190	180-190	180-190	180-190	180-190	50-70

