

## PP P1235WE

Features	Applications
<ul style="list-style-type: none"> <li>➤</li> <li>➤</li> <li>➤</li> <li>➤</li> </ul>	<ul style="list-style-type: none"> <li>➤</li> <li>➤ &amp;</li> </ul>

Properties	Test Method	Test Condition	Unit	Typical value
<b>Physical</b>				
Specific Gravity	ISO 1183	23	g/cm <sup>3</sup>	1.15
Mold Shrinkage	ISO 294	23	%	0.9-1.4
<b>Mechanical</b>				
Tensile Strength	ISO 527	50mm/min	MPa	25
Flexural Modulus	ISO 178	2mm/min	MPa	2300
Notched Izod Impact (23 )	ISO 180	2.75J	kJ/m <sup>2</sup>	5.5
Notched Izod Impact (-20 )	ISO 180	2.75J	kJ/m <sup>2</sup>	3.5
<b>Thermal</b>				
Heat Distortion Temp.	ISO 75	0.45MPa		115