

◇	◇
◇	◇

Properties	Test Method	Test Condition	Unit	W7001
Physical				
Density		23	g/cm ³	1.2
Melt Flow Rate		220	g/10min	
Mold Shrinkage		23	%	
Mechanical				
Tensile Strength		50mm/min	MPa	38
Tensile Strain @ break		50mm/min	%	5
Flexural Strength		2mm/min	MPa	65
Flexural Modulus		2mm/min	GPa	2.4
Notched Charpy Impact Strength			KJ/m ²	8
Thermal				
Heat deflection temperature		0.45MPa		90
Flammability				
Vertical Burn		1.6mm		V-0

✓

✓

265700

0535-8828888

0535-8833788