

Dawnprene TPE 9501-PB

TPE

TPE

Features: It is a black thermoplastic elastomer (TPE) material. This material combines good physical properties, chemical resistance and elasticity, designed for injection applications. This grade of TPE can be processed on conventional thermoplastics equipment for injection. It is completely recyclable.

RoHS	RoHS		
	2023-03-28		
	0.91	g/cm ³	ASTM D792
(Shore D,5sec,2	43	D	ASTM D2240
100% 2	9.71	Mpa	ASTM D412
2	15.8	Mpa	ASTM D412
2	670	%	ASTM D412
2	79	KN/m	ASTM D624

0.1%

Drying Instructions: Need drying the granules before make molding, excessive moisture will lead materials bad extrusion surface, mechanical performance reduction and bad surface appearance. Moisture content request below 0.1%, suggesting drying as follow process:

Drying conditions	Drying temperature/	Drying time/h
first choice	80 90	2 3
other choice	100	1

110

105

If drying temperature over than 110 ,it might cause materials blocking in barrel zone;if use moisture analysis meter,the temperature setting should be on 105 .



R							
4	16 170	180-230	180-230	180-230	180-230	180-230	50-70

1.Dawnprene TPE PVC Dawnprene TPE is incompatible with PVC materials,hence must clean the equipment before using.
2. The properties is typical performance,is not regarding as technical index or agreement.
3. Any reprocessing must follow the above instructions,and ensure no content impurity.
4. Above instructions for reference only,different equipment might have difference parameters,please adjust accordingly with different mold and product shape.
SHANDONG DAWN POLYMER CO.,LTD : Address:Zhenxing Road,Longgang Economic Zone,Longkou,Shandong, China. 265703 () 0086-535-8868588;()0086-535-8833988 Tel:(Foreign Trade) 0086-535-8868588;(Domestic Trade)0086-535-8833988